

# Technical data sheet PLA

Ultimaker

<b>Chemical composition</b>	See PLA safety data sheet, section 3
<b>Description</b>	Ultimaker PLA filament provides a no-hassle 3D printing experience thanks to its reliability and good surface quality. Our PLA is made from organic and renewable sources. It's safe, easy to print with, and it serves a wide range of applications for both novice and advanced users
<b>Key features</b>	Good tensile strength and surface quality, easy to work with at high print speeds, user-friendly for both home and office environments, PLA allows the creation of high-resolution parts. There is a wide range of color options available
<b>Applications</b>	Household tools, toys, educational projects, show objects, prototyping, architectural models, as well as lost casting methods to create metal parts
<b>Non-suitable for</b>	Food contact and <i>in vivo</i> applications. Long term outdoor usage or applications where the printed part is exposed to temperatures higher than 50 °C

## Filament specifications

	<b>Value</b>	<b>Method</b>
<b>Diameter</b>	2.85 ± 0.10 mm	-
<b>Max roundness deviation</b>	0.10 mm	-
<b>Net filament weight</b>	350 g / 750 g	-
<b>Filament length</b>	~ 44 m / ~ 95 m	-

## Color information

<b>Color</b>	<b>Color code</b>
PLA Green	RAL 6018
PLA Black	RAL 9005
PLA Silver Metallic	RAL 9006
PLA White	RAL 9010
PLA Transparant	N/A
PLA Orange	RAL 2008
PLA Blue	RAL 5002
PLA Magenta	RAL 4010
PLA Red	RAL 3020
PLA Yellow	RAL 1003
PLA Pearl White	RAL 1013

## Mechanical properties\*

	Injection molding		3D printing	
	Typical value	Test method	Typical value	Test method
Tensile modulus	-	-	2,346.5 MPa	ISO 527 (1 mm/min)
Tensile stress at yield	-	-	49.5 MPa	ISO 527 (50 mm/min)
Tensile stress at break	-	-	45.6 MPa	ISO 527 (50 mm/min)
Elongation at yield	-	-	3.3%	ISO 527 (50 mm/min)
Elongation at break	-	-	5.2%	ISO 527 (50 mm/min)
Flexural strength	-	-	103 MPa	ISO 178
Flexural modulus	-	-	3,150 MPa	ISO 178
Izod impact strength, notched (at 23 °C)	-	-	5.1 kJ/m <sup>2</sup>	ISO 180
Charpy impact strength (at 23 °C)	-	-	-	
Hardness	-	-	83 (Shore D)	Durometer

## Electrical properties\*

	Typical value	Test method	Typical value	Test method
Dissipation factor (at 1 MHz)	-	-	0.008	ASTM D150-11
Dielectric constant (at 1 MHz)	-	-	2.70	ASTM D150-11

## Thermal properties

	Typical value	Test method
Melt mass-flow rate (MFR)	6.09 g/10 min	ISO 1133 (210 °C, 2.16 kg)
Heat detection (at 0.455 MPa)	-	-
Heat deflection (at 1.82 MPa)	-	-
Vicat softening temperature	-	-
Glass transition	~ 60 °C	ISO 11357
Coefficient of thermal expansion	-	-
Melting temperature	145 - 160 °C	ISO 11357
Thermal shrinkage	-	-

\*See notes

## Other properties

	<b>Value</b>	<b>Test method</b>
<b>Specific gravity</b>	1.24	ASTM D1505
<b>Flame classification</b>	-	-

## Notes

Properties reported here are average of a typical batch. The 3D printed test specimens were printed in the XY plane, using the normal quality profile in Ultimaker Cura 2.1, an Ultimaker 2+, a 0.4 mm nozzle, 90% infill, 210 °C nozzle temperature, and 60 °C. The values are the average of five white and five black specimens for the tensile, flexural, and impact tests. The Shore hardness D was measured in a 7-mm-thick square printed using the normal quality profile in Ultimaker Cura 2.5, an Ultimaker 3, a 0.4 mm print core, and 100% infill. The electrical properties were measured on a 54-mm-diameter disk with 3 mm thickness printed in the XY plane, using the fine quality profile (0.1 mm layer height) in Ultimaker Cura 3.2.1, an Ultimaker 3, a 0.4 mm print core, and 100% infill. Ultimaker is constantly working on extending the TDS data.

## Disclaimer

Any technical information or assistance provided herein is given and accepted at your risk, and neither Ultimaker nor its affiliates make any warranty relating to it or because of it. Neither Ultimaker nor its affiliates shall be responsible for the use of this information, or of any product, method or apparatus mentioned, and you must make your own determination of its suitability and completeness for your own use, for the protection of the environment, and for the health and safety of your employees and purchasers of your products. No warranty is made of the merchantability or fitness of any product; and nothing herein waives any of Ultimaker's conditions of sale. Specifications are subject to change without notice.

<b>Version</b>	Version 4.002
<b>Date</b>	November 19, 2018